



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number: **0 423 602 A1**

EUROPEAN PATENT APPLICATION

(12)

(21) Application number: **90119387.0**

(51) Int. Cl.⁵: **C08K 3/16, C08L 71/12**

(22) Date of filing: **10.10.90**

(30) Priority: **20.10.89 US 424641**

(43) Date of publication of application:
24.04.91 Bulletin 91/17

(84) Designated Contracting States:
DE ES FR GB IT NL

(71) Applicant: **GENERAL ELECTRIC COMPANY**
1 River Road
Schenectady, NY 12345(US)

(72) Inventor: **Axelrod, Robert Jay**
4138 Willow Way
Orefield, Pennsylvania 18069(US)

(74) Representative: **Schüler, Horst, Dr. et al**
Kaiserstrasse 69
W-6000 Frankfurt/Main 1(DE)

(54) **Antistatic PPE compositions and methods.**

(57) Thermoplastic polymer compositions comprise a polyphenylene ether resin and an alkali metal chloride in an amount sufficient to provide the composition with antistatic properties. Preferably, the alkali metal chloride comprises lithium chloride and is included in an amount of from about 0.5 to about 15 parts by weight per hundred parts by weight resin.

EP 0 423 602 A1

BEST AVAILABLE COPY

ANTISTATIC PPE COMPOSITIONS AND METHODS

FIELD OF THE INVENTION

The present invention relates to polyphenylene ether resin compositions which exhibit antistatic properties. The present invention also relates to methods for providing polyphenylene ether resin compositions with antistatic properties. Throughout the present disclosure, reference to antistatic properties refers to the ability of a material to dissipate electrostatic charge.

BACKGROUND OF THE INVENTION

Thermoplastic polymer compositions which are electrically insulating tend to accumulate very high electrostatic potentials via triboelectric generation and therefore are disadvantageous for use in many applications. For example, when such compositions are employed in electronic equipment, the static electric charge can accumulate and permanently damage sensitive integrated circuits if one or more parts formed of the electrically insulating polymer compositions are grounded through the integrated circuits.

Accordingly, resin compositions which exhibit antistatic properties and dissipate electrostatic charge are advantageous for use in various applications in the electronics industry including devices employing integrated circuit components, housings for computer components and other electrical equipment, smoke detectors which employ electrically polarized ionization chambers, and the like. Antistatic resins have been prepared by including one or more antistatic additives in the resin compositions. Generally, these additives are derivatives of quaternary ammonium salts and contain thermally unstable, hygroscopic functionalities such as polyethylene oxide radicals. The use of the hygroscopic groups is based on the theory that the antistatic effect is provided by a conductive surface layer on the resin which is formed from a water solution of organic ions. Resins having antistatic properties generally exhibit surface resistivities of 10^8 to 10^{10} ohm/cm² and a static decay time of less than two seconds as measured by Military Specification MIL-B-81705B.

Generally, however, it has been difficult to provide antistatic properties to high performance engineering resins such as polyphenylene ether resin compositions since such resins are processed at relatively high temperatures which degrade conventional antistatic additives.

SUMMARY OF THE INVENTION

Accordingly, it is an object of the present invention to provide thermoplastic polymer compositions which exhibit antistatic properties. It is a further object of the invention to provide high performance polyphenylene ether resin compositions which exhibit antistatic properties. It is an additional object of the invention to provide such compositions which exhibit such antistatic properties after repeated water washings. It is a further object of the invention to provide antistatic polyphenylene ether resin compositions which also exhibit environmental stress crack resistance. A further object of the present invention is to provide methods for rendering thermoplastic polymer compositions comprising polyphenylene ether resins antistatic.


These and additional objects are provided by the thermoplastic polymer compositions of the present invention which comprise a polyphenylene ether resin and an alkali metal chloride. The alkali metal chloride is included in an amount sufficient to provide the composition with antistatic properties. In a preferred embodiment, the alkali metal chloride comprises lithium chloride. The compositions according to the present invention exhibit good antistatic properties, even after repeated water washings, and environmental stress crack resistance. In an additional preferred embodiment, the compositions of the invention further include a styrene resin which provides the compositions with a more advantageous combination of overall physical and chemical properties.

These and additional objects and advantages provided by the compositions and methods of the present invention will be more fully understood in view of the following detailed description.

DETAILED DESCRIPTION

The present thermoplastic polymer compositions comprise a polyphenylene ether resin and an alkali metal chloride in an amount sufficient to provide the composition with antistatic properties.

Polyphenylene ether resins adapted for use in the polymer compositions of the present invention comprise polymers and copolymers having repeating structural units of the following general formula:




wherein each R individually represents a monovalent substituent such as hydrogen, halogen, alkyl, aryl, alkoxy and other hydrocarbon groups, r is from 1 to 4, and n represents the degree of polymerization. Preferably, n is at least 20, and more preferably, n is at least 50.

The polyphenylene ether resins suitable for use in the polymer compositions of the present invention are well known in the art and may be prepared by any of a number of processes known in the art from corresponding phenols or reactive derivatives thereof. Examples of polyphenylene ether resins and methods for their production are set forth in the Hay U.S. patents Nos. 3,306,874 and 3,306,875 and in the Stamatoff U.S. patents Nos. 3,257,357 and 3,257,358, all of which are incorporated herein by reference. Throughout the Specification and Claims the term "polyphenylene ether" includes unsubstituted polyphenylene ether polymers, substituted polyphenylene ether polymers and polyphenylene ether copolymers.

Preferred polyphenylene ether resins adapted for use in the polymer compositions of the present invention include, but are not limited to, poly(2,6-dimethyl-1,4-phenylene)ether; poly(2,6-diethyl-1,4-phenylene)ether; poly(2-methyl-6-ethyl-1,4-phenylene)ether; poly(2-methyl-6-propyl-1,4-phenylene)ether; poly(2,6-dipropyl-1,4-phenylene)ether; poly(2-ethyl-6-propyl-1,4-phenylene)ether; poly(2,6-dilauryl-1,4-phenylene)ether; poly(2,6-diphenyl-1,4-phenylene)ether; poly(2,6-dimethoxy-1,4-phenylene)ether; poly(2,6-diethoxy-1,4-phenylene)ether; poly(2-methoxy-6-ethoxy-1,4-phenylene)ether; poly(2-ethyl-6-stearyloxy-1,4-phenylene)ether; poly(2,6-dichloro-1,4-phenylene)ether; poly(2-methyl-6-phenyl-1,4-phenylene)ether; poly(2,6-dibenzyl-1,4-phenylene)ether; poly(2-ethoxy-1,4-phenylene)ether; poly(2-chloro-1,4-phenylene)ether; poly(2,6-dibromo-1,4-phenylene)ether; copolymers thereof, and the like.

The alkali metal chloride compound which is included in the thermoplastic polymer compositions of the present invention is employed in an amount sufficient to provide the compositions with antistatic properties. Generally, the inclusion of from about 0.5 to 15 parts by weight of the alkali metal chloride per 100 parts by weight resin provides the composition with antistatic properties characterized by surface resistivities of 10^8 to 10^{10} ohm/cm² and static decay times of less than two seconds. In a preferred embodiment, the alkali metal chloride is included in an amount of from about 1 to about 5 parts by weight per 100 parts by weight resin. It is additionally preferred that the alkali metal chloride comprises lithium chloride, although other alkali metal chlorides may be employed alone or in combination with the lithium chloride. It is believed that the thermal stability and hygroscopic property of the lithium chloride assist in imparting the antistatic properties to the present compositions. As will be exhibited in the examples set forth below, the antistatic properties of the present polymer compositions are retained, even after repeated water washings. Additionally, it has been discovered that the lithium chloride also provides the resulting thermoplastic polymer compositions with improved environmental stress crack resistance.

In a preferred embodiment, the thermoplastic polymer compositions further include a styrene resin. Various styrenes resins are well known in the art and preferably comprise at least 25 weight percent polymer units derived from a styrene monomer having the following formula:



wherein R_1 and R_2 are selected from the group consisting of lower alkyl or alkenyl groups of from, for example, 1 to 6 carbon atoms and hydrogen, each R_3 is selected from the group consisting of halogen, hydrogen and lower alkyl or alkenyl groups of from, for example, 1 to 6 carbon atoms, and a is an integer of from 0 to 5. Throughout the specification and claims the term "polystyrene resin" includes unsubstituted polystyrene, substituted polystyrene and polystyrene copolymer resins. For example, suitable polystyrene resins include, but are not limited to, homopolymers of polystyrene, polychlorostyrene, polymethylstyrene and the like, and styrene-containing copolymers such as styrene-acrylonitrile copolymers, copolymers of ethyl vinyl benzene and divinyl benzene, styrene-acrylonitrile-methylstyrene terpolymers and the like. The methods for preparing these polystyrenes are well known in the art.

Preferably, the styrene resin comprises a high impact polystyrene resin containing an impact modifier. The impact modifier included in the high impact polystyrene resins serves to improve the impact properties of the polymer compositions. Impact modifiers are well known in the art and generally comprise rubber or elastomeric compounds. Both natural and synthetic rubber and elastomeric compounds are suitable for use in the high impact polystyrene resins. For example, suitable impact modifiers include homopolymers or copolymers of one or more monomers such as butadiene, isoprene and ethylene-propylene diene monomers. Additional impact modifiers for use in the present invention include, but are not limited to, hydroxy- and carboxy-terminated polybutadienes, polychlorobutadienes, copolymers of dienes such as butadiene and isoprene with various comonomers such as alkyl unsaturated esters, for example methylmethacrylate, unsaturated ketones, for example methylisopropenyl ketone, vinyl heterocyclics, for example vinyl pyridine, and the like. Other impact modifiers known in the art may also be used according to the present invention. Preferably, the impact modifier and the polystyrene resin which are combined to form the high impact polystyrene resin are combined prior to mixing with the other composition ingredients. Additionally, the polystyrene resin and the impact modifier are preferably combined in a ratio of at least 3:1 by weight to form the high impact polystyrene resin which is then blended with the polyphenylene ether and the remaining composition ingredients.

When the thermoplastic polymer compositions comprise both a polyphenylene ether resin and a styrene resin, it is preferred that the polyphenylene ether resin is included in an amount of from about 10 to about 90 parts by weight, more preferably about 20 to about 80 parts by weight, and that the styrene resin is included in an amount of from about 10 to about 90 parts by weight, preferably from about 20 to about 80 parts by weight. The alkali metal chloride is also preferably included in these compositions in an amount of from about 0.5 to about 15 parts by weight per 100 parts by weight resins.

The thermoplastic polymer compositions may also include conventional ingredients known in the art. For example, the compositions may include an additional impact modifier in order to further improve the impact strength of the compositions. Impact modifiers for polyphenylene ether resin compositions are well known in the art and include, but are not limited to, the following: natural rubber, butadiene polymers, butadiene/styrene copolymers, isoprene polymers, chlorobutadiene polymers, butadiene/acrylonitrile copolymers, isobutylene polymers, isobutylene/butadiene copolymers, isobutylene/isoprene copolymers, acrylic ester polymers, ethylene/propylene copolymers, ethylene/propylene/diene copolymers, thiokol rubber, polysulfide rubber, polyurethane rubber, polyether rubber (e.g., polypropylene oxide), epichlorohydrin rubber, hydrogenated or non-hydrogenated block copolymers of the A-B-A and A-B type wherein A is polystyrene and B is an elastomeric diene, e.g., polybutadiene, radial teleblock copolymers of styrene and a conjugated diene, acrylic resin modified styrene-butadiene resins, thermoplastic polyester elastomers, thermoplastic polyether-ester elastomers, ethylenic ionomer resins, and the like. Preferably, such impact modifiers are included in an amount of from about 1 to about 30 parts by weight, per 100 parts by weight total resins.

Additionally, conventional amounts of conventional additives for processability, stability and the like, including color stabilizers, thermal stabilizers, fire retardants and the like, may be included in the polymer

compositions of the present invention. Fillers and/or reinforcing fillers may also be included in the compositions in a conventional manner.

The compositions of the present invention including the alkali metal chloride exhibit improved antistatic properties which are retained even after repeated washings with water, even in an ultrasonic bath. The antistatic properties are particularly desirable for injection molding the polymer compositions whereby the injection molded parts may be used in various applications in the electronics industry.

The following examples are provided to illustrate specific embodiments of the present invention.

EXAMPLE 1

In this example, polyphenylene ether resin Compositions 1-8 were prepared, Compositions 1-7 being according to the present invention and Composition 8 being a comparative composition. Each composition contained 50 parts by weight polyphenylene ether resin, 50 parts by weight high impact polystyrene, 15 parts by weight of a trialkaryl phosphate flame retardant, 1.5 parts by weight polyethylene, 0.5 parts by weight of a phosphite color stabilizer and 0.15 parts by weight each of zinc oxide and zinc sulfide. Compositions 1-7 according to the present invention also included lithium chloride, the amount of which included in each composition is set forth in Table I. Comparative Composition 8 did not contain any lithium chloride. Each of Compositions 1-8 were subjected to measurement of melt viscosity (540°F, 1500 sec⁻¹), according to ASTM D-3835-79, heat distortion temperature (2.5 x 0.5 x 1/8-inch bars), according to ASTM D-648, Izod impact (2.5 x 0.5 x 1/8-inch bar) according to ASTM D-256 and tensile properties (1/8-inch tensile bars) according to ASTM D-638. The samples were molded at 500/150 with a melt temperature of approximately 530°F. The compositions were also subjected to measurement of their mold filling capabilities using a flow channel test employing a 1/4-inch channel and an injection molding temperature of approximately 530°F. The results of these measurements are set forth in Table I.

TABLE I

Composition	1	2	3	4	5	6	7	8
LiCl, parts by weight	0.1	0.3	0.5	1.0	1.5	2.0	3.0	—
Melt Viscosity, Poise	997	996	1010	1012	1054	1046	1109	1135
Flow Channel, inches	21	20.5	20.5	21	20.5	20.5	20	20
Heat Distortion Temp., °F	186	186	187	187	186	186	189	186
Izod Impact, ft-lb/in.	4.6	4.2	3.7	2.8	2.5	2.2	1.8	5.2
Tensile Yield, psi	7.9	7.9	7.9	7.9	7.9	7.7	7.9	8.0
Tensile Strength, psi	7.1	7.1	7.0	7.0	5.8	6.9	7.0	7.4
Elongation, %	71	59	56	46	47	55	46	87

The results set forth in Table I demonstrate that the polymer compositions according to the present invention exhibit a good combination of physical properties. While the addition of lithium chloride appears to decrease the Izod impact of the compositions, this property can be improved by the use of thermoplastic elastomer impact modifiers and/or by reducing the particle size of the lithium chloride included therein.

EXAMPLE 2

A further Composition 9 according to the present invention was prepared comprising 20 parts by weight polyphenylene ether resin, 80 parts by weight dibromostyrene polymer, 1.5 parts by weight polyethylene, 5 parts by weight antimony oxide and 0.15 parts by weight each of zinc oxide and zinc sulfide. Composition 9 also included 1.5 parts by weight lithium chloride. This composition was molded and subjected to measurement in accordance with the procedures described in Example 1. The composition exhibited a melt viscosity of 1276 poise, a flow channel of 21.5 inches, a heat distortion temperature of 216°F, an Izod impact of 2.0 ft. lb/in., a tensile yield of 6.6 psi, a tensile strength of 6.6 psi and a tensile elongation of 47 percent.

EXAMPLE 3

Molded samples of Compositions 1-9 were subjected to several tests to evaluate their antistatic properties. Using Federal Test Method 4046, Standard 101B, the static decay and surface resistivity of the compositions were determined. During each test, 5,000 volts were employed and the respective sample was shorted to ground. The tests were conducted under conditions of 15% or lower relative humidity. Directly after molding, samples of each composition were placed in airtight plastic bags and were not exposed to ambient air or humidity. None of the compositions exhibited charge decay, presumably owing to lack of moisture pickup under the anhydrous storage and test conditions. Similar samples of the compositions were allowed to sit for 48 hours at room temperature and humidity (approximately 50-60% relative humidity). The samples were then tested for residual charge, acceptance of full charge and decay rate (time to decay to 10 percent of original charge). The results of these tests are set forth in Table II.

TABLE II

Composition	LiCl	Residual Charge	Accepted Full Charge	Decay Rate, sec.
1	0.1	Yes	No	∞
2	0.3	Yes	No	∞
3	0.5	Yes	No	∞
4	1.0	No	Yes	.05
5	1.5	No	Yes	.05
6	2.0	No	Yes	.05
7	3.0	No	Yes	.05
8	—	Yes	No	∞
9	1.5	No	Yes	.05

Additional molded samples were washed with water, dried with a cloth and then subjected to the above-described test procedures. The results of these tests are set forth in Table III.

TABLE III

Composition	LiCl	Residual Charge	Accepted Full Charge	Decay Rate, sec.
1	0.1	Yes	No	∞
2	0.3	Yes	No	∞
3	0.5	Yes	No	∞
4	1.0	Yes	No	∞
5	1.5	Slight	Yes	.05 to residual charge
6	2.0	No	Yes	.21
7	3.0	No	Yes	.05
8	—	Yes	No	∞
9	1.5	Slight	No	∞

Finally, the samples were subjected to washing in a dishwasher. The washed samples were wiped clean and dried and then again tested according to the above-described procedures. The results of these tests are set forth in Table IV.

TABLE IV

Composition	LiCl	Residual Charge	Accepted Full Charge	Decay Rate, sec.
1	0.1	Yes	No	∞
2	0.3	Yes	No	∞
3	0.5	Slight (8%)	No	∞
4	1.0	No	Yes	.25
5	1.5	No	Yes	.05
6	2.0	No	Yes	.04
7	3.0	No	Yes	.05
8	—	Yes	No	∞
9	1.5	No	Yes	.05

The test results set forth above demonstrate that between 0.5 and 1.0 parts by weight of lithium chloride per 100 parts by weight resin was required in order for the compositions to exhibit static dissipation. The above test results also demonstrate that the antistatic properties are retained, even after washing, when at least about 1 part by weight of lithium chloride is employed per 100 parts by weight resin. Additionally, sufficient lithium chloride was retained after vigorous washing to maintain the antistatic properties.

Generally, conditioning the as molded samples for approximately two hours at 15 percent relative humidity prior to conducting the described tests was sufficient to hydrate the samples whereby the antistatic properties could be determined.

EXAMPLE 4

Polymer Compositions 11 and 12 were prepared generally as described in Example 1 containing 1 part by weight lithium chloride and 3 parts by weight lithium chloride, respectively, per 100 parts by weight resin. The environmental stress crack resistance of the compositions was then determined according to the following procedure. Molded samples were formed in a relatively cold mold in order to simulate high levels of environmental stress. The samples were then positioned in a strain jig in which a portion of the sample was bent around a curved portion of the jig. A strain inducer comprising the liquid trialkaryl phosphate flame retardant was painted on the bent sample and the sample was then maintained in the strain jig for a period of time T. For each period of time T, five samples of each of Compositions 11 and 12 were tested. Afterward, each sample was examined to determine if cracks occurred in the tested sample. Samples of Comparative Composition 8 described in Example 1 and containing no lithium chloride were also tested. The results of these tests are set forth in Table V. In Table V, the percent cracked value refers to the percentage of the five samples tested, whereby 20 percent indicates that one of the five samples cracked, 40 percent indicates that two of the five samples cracked, etc.

TABLE V

T, Hours	Composition 8 (no LiCl), % cracked	Composition 11 (1% LiCl), % cracked	Composition 12, (3% LiCl), % cracked
0	0	0	0
0.5	0	20	0
1	40	20	0
3	60	100	0
6	80	100	0
23	100	100	0
30	100	100	0
46	100	100	0

These results demonstrate that the addition of small amounts, for example 3 weight percent, of lithium chloride to polyphenylene ether resin compositions also provides an improved effect on the resins' environmental stress crack resistance.

- 5 The preceding examples are set forth to illustrate specific embodiments of the invention and are not intended to limit the scope of the compositions and methods of the present invention. Additional embodiments and advantages within the scope of the claimed invention will be apparent to one of ordinary skill in the art.

10

Claims

1. A thermoplastic polymer composition, comprising a polyphenylene ether resin and an alkali metal chloride in an amount sufficient to provide the composition with antistatic properties.
- 15 2. A thermoplastic polymer composition as defined by claim 1, comprising from about 0.5 to about 15 parts by weight of the alkali metal chloride per hundred parts by weight resin.
3. A thermoplastic polymer composition as defined by claim 2, wherein the alkali metal chloride comprises lithium chloride.
4. A thermoplastic polymer composition as defined by claim 1, further comprising a styrene resin.
- 20 5. A thermoplastic polymer composition as defined by claim 4, wherein the styrene resin comprises a high impact polystyrene resin containing an impact modifier.
6. A thermoplastic polymer composition as defined by claim 4, comprising from about 10 to about 90 parts by weight of the polyphenylene ether resin and from about 10 to about 90 parts by weight of the styrene resin, and from about 0.5 to about 15 parts by weight of the alkali metal chloride per hundred parts by weight resins.
- 25 7. A thermoplastic polymer composition as defined by claim 6, comprising from about 1 to about 5 parts by weight of the alkali metal chloride per hundred parts by weight resins.
8. A thermoplastic polymer composition as defined by claim 6, comprising from about 20 to about 80 parts by weight of the polyphenylene ether resin and from about 20 to about 80 parts by weight of the styrene resin.
- 30 9. A thermoplastic polymer composition as defined by claim 4, further comprising an additional thermoplastic impact modifier.
10. A thermoplastic polymer composition as defined by claim 9, wherein the thermoplastic elastomer is included in an amount sufficient to improve the impact strength of the composition.
- 35 11. A method for providing a thermoplastic polymer composition comprising a polyphenylene ether resin with antistatic properties, said method comprising adding to the composition an alkali metal chloride in an amount sufficient to provide the composition with antistatic properties.
12. A method as defined by claim 11, wherein the alkali metal chloride is added in an amount of from about 0.5 to about 15 parts by weight per hundred parts by weight resin.
- 40 13. A method as defined by claim 11, wherein the alkali metal chloride comprises lithium chloride.
14. A method as defined by claim 11, wherein the thermoplastic polymer composition further comprises a styrene resin.
15. A method as defined by claim 14, wherein the styrene resin comprises a high impact polystyrene resin containing an impact modifier.

45

50

55

EP 90 11 9387

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. CL5)
A	US-A-4 746 697 (N. YAMAGUCHI ET AL) * column 2, lines 38 - 50 * * column 4, lines 49 - 59; example 6 *	1	C 08 K 3/16 C 08 L 71/12
X	DA-T- (HOST:STN)ref.no. 110(20): 174496w, Columbus, Ohio & JP-A-63 304060 (NIPPON SYNTHETIC CHEMICAL INDUSTRY CO.) 12-12-1988 * whole abstract *	1-15	
			TECHNICAL FIELDS SEARCHED (Int. CL5)
			C 08 K C 08 L
The present search report has been drawn up for all claims			
Place of Search The Hague		Date of completion of search 01 February 91	Examiner HOFFMANN K.W.
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention		E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document	

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record.**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.